

# Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

---

---

ARL-TR-2484

May 2001

## Processing and Characterization of Welded Bonds Between Thermoset and Thermoplastic Composites

Stephen H. McKnight and Bruce K. Fink  
Weapons and Materials Research Directorate, ARL

Veronique Monnard, P.-E. Bourban, and Jan-Anders E. Manson  
Swiss Federal Institute of Technology

Douglas A. Eckel, II and John W. Gillespie, Jr.  
University of Delaware

---

## Abstract

---

To assemble complex structures with short cycle times, the feasibility of welding thermoplastic (TP) to thermoset (TS) composites is demonstrated using a phenomenological approach. The effect of the thermal degradation of the TS composite (AS4/3501-6) on its shear strength is assessed in order to minimize the TS degradation during the welding process. The degradation is reported to decrease the shear strength in an exponential way. A layer of TP (polysulphone [PSU]) is cocured at the surface of the AS4/3501-6 laminate during its cure cycle in an autoclave. Two laminates are then welded together using a resistance welder. The highest shear strengths, which are close to the shear strength of bulk AS4/3501-6 autoclave-processed baseline, occur for a welding time and temperature of 10 s and 300 °C, respectively. Higher and lower temperatures induce degradation and low consolidation of the weld, respectively. The welding interface between the TP layers is the strongest, while failure is mixed and occurs at interfaces between TS and TP and at interfaces between TP and heating element at the fiber/matrix interfaces. Further investigations are required to optimize the welding processing parameters and to identify the bonding, degradation, and failure mechanisms using a more fundamental and molecular approach.

# Table of Contents

	<u>Page</u>
<b>List of Figures</b> .....	v
<b>List of Tables</b> .....	vii
<b>1. Introduction</b> .....	1
1.1 Thermoset/Thermoplastic Bonds .....	1
1.2 Thermoplastic/Thermoplastic Bonds .....	2
1.3 Approach .....	2
<b>2. Experimental</b> .....	3
2.1 Materials.....	3
2.2 Thermal Degradation.....	4
2.3 Processing.....	4
2.4 Welding .....	4
2.5 Testing.....	5
<b>3. Results and Discussion</b> .....	5
3.1 Degradation .....	5
3.2 Thermoset/Thermoplastic Bond Quality .....	7
3.3 Welding Properties .....	7
3.4 Failure Mechanisms .....	10
<b>4. Conclusion</b> .....	11
<b>5. References</b> .....	13
<b>Distribution List</b> .....	15
<b>Report Documentation Page</b> .....	33

INTENTIONALLY LEFT BLANK.

# List of Figures

<u>Figure</u>	<u>Page</u>
1. Resistance-Welding Process .....	3
2. Effect of Thermal Degradation on the Bulk AS4/3501-6 Baselines .....	6
3. Results of Two Typical Good-Quality Welds With a Shear Strength Close to the Bulk AS4/3501-6 Baseline.....	8
4. Results of Four Typical Poor-Quality Welds at Low Consolidation Temperature .....	8
5. Results of Four Typical Welds Evidencing the Inhomogeneity of Thermal History Influencing the Distribution of the Bond Strengths.....	9
6. Good-Quality Weld (NSS = 1).....	10
7. Degraded Weld (NSS = 0.5) .....	10
8. Typical Mixed Failure of the Weld .....	11

INTENTIONALLY LEFT BLANK.

# List of Tables

<u>Table</u>	<u>Page</u>
1. Differences of Weight Losses Between TGA and Degradation in an Oven for Several Exposure Conditions .....	6

INTENTIONALLY LEFT BLANK.

# 1. Introduction

This report studies the feasibility of a new technique whose advantages overcome the drawbacks of using mechanical fasteners or chemical adhesives for joining thermoset (TS) composites. Furthermore, this technique, called fusion bonding, allows two TS parts to be joined in shorter time, with the possibility of future disassembly of the complex bonded structures. This technique has already been applied to join thermoplastic (TP) composites, but can reasonably be applied to join TS when a layer of TP is cocured on the surfaces to be joined. Subsequently, two types of interfaces are then responsible for the strength of the final piece, that is to say, the TS/TP interface and the TP/TP joining interface.

**1.1 Thermoset/Thermoplastic Bonds.** The bonding between a TS and TP is dictated by the chemical compatibility of the two materials. The degree of chemical compatibility can be defined by a unique glass transition temperature ( $T_g$ ) or by two similar solubility parameters ( $\delta$ ). Indeed, the square of the difference between the  $\delta$  of the two materials is directly related to the enthalpy of mixing  $\Delta H_m$ . In order to have a spontaneous mixing, the Gibbs free energy of mixing ( $\Delta G_m$ ) has to be minimized; this is reached by minimizing  $\Delta H_m$  and occurs when the two  $\delta$  are similar. Once a TS and TP are chemically compatible, they can form an interpenetrating polymer network (IPN) [1] in order to ensure a high enough bond strength. This occurs during the cure cycle of the TS, whose monomers diffuse into the molecular chains of the TP [2] and form a three-dimensional network or IPN.

In the case of good chemical compatibility between the TS and TP materials, the technique of the film cocuring is used most often [2] to bond the TP film on the TS part during its cure cycle in an autoclave. In the case of chemical incompatibility, a new technique was recently developed, termed diffusion-enhanced adhesion (DEA) [3], and consists of adding a second TP film (TP2) at the TS/TP interface, which is chemically compatible with the TS and has a  $T_g$  close to the one of the TP. A last technique, less commonly used, is the TP hybrid interlayer that does not require chemical compatibility because the bonding is purely mechanical. The TS is bonded


to a carbon fiber-based TP (CF/TP), whose face to be bonded contains only an empty fibrous network in which the TS will diffuse during the curing [4].

**1.2 Thermoplastic/Thermoplastic Bonds.** Bonds between two TPs are more easily achieved because of the same nature of the materials, which can be easily molten during fusion bonding. However, there are still some bonding mechanisms to consider in order to control the bond quality. First, the two materials to be bonded require some degree of intimate contact, which is defined as the percentage of area that is in contact with the two surfaces to be bonded. Then, in a process called healing, an interdiffusion of the chains takes place and forms an entanglement of the chains. This is the reason for the high strength of the bond, similar to an IPN in the case of TS/TP bonds. During the last step, the consolidation pressure is applied in order to reduce the voids and reach an optimum thickness of the bond, which is achieved by squeeze flow of the TP.

Some processes developed for bonding two TPs together, such as the thermabond method [5], have been used with techniques like press or resistance welding. In the case of TS/TP welding, whose process is described in Figure 1, the temperature has to be between the  $T_g$  and the melting temperature ( $T_m$ ) of the TP, but below the temperature at which the TS degrades.

A schematic of the resistance-welding process is shown in Figure 1; two CF/TS parts containing a cocured layer of TP are welded using an interlayer heating element. An alternating current source is applied to the heating element through its ends. Due to the Joule effect, the heating element gets hot enough to allow the two parts' surfaces to melt and be welded. Additionally, pressure is applied to ensure a good contact and consolidation during the cooling stage.

**1.3 Approach.** A phenomenological approach was followed in this work, which contained three different steps. The first step was related to the materials (TS and TP), which had to be



**Figure 1. Resistance-Welding Process.**

chosen in order to be chemically compatible to form an IPN. Furthermore, the TS needs to be sufficiently resistant to thermal degradation during welding. For this purpose, the effect of thermal degradation on mechanical properties of the TS was assessed first. The second step was processing the cocured TP layer on the TS part, followed by fusion bonding the two parts using a resistance-welding technique. The final step was the characterization of the welds by assessing the interfacial shear strength and the observation of the failure mechanisms.

## 2. Experimental

**2.1 Materials.** The TS used in this work was a unidirectional carbon fibers/epoxy (AS4/3501-6) from Magnamite Hercules, with a  $T_g$  of 215 °C. The TP was a polysulphone (PSU), with a  $T_g$  of 185 °C and a processing temperature between 300 °C and 360 °C. These materials have both good chemical compatibility and bonding quality [3], but AS4/3501-6 is also a commonly used TS for high-performance applications despite low thermal degradation

resistance. PSU has a high melt viscosity and a high temperature resistance. Furthermore, PSU has shown good welding properties in earlier applications [6].

**2.2 Thermal Degradation.** Thermal degradation of AS4/3501-6 is not yet well understood. In order to measure weight loss, several bulk AS4/3501-6 baseline specimens were degraded in a conventional oven, under vacuum, and at different temperatures and times going from 250 °C to 345 °C and from 10–60 min, respectively. The chosen temperatures and times were determined from isothermal thermogravimetric analysis (TGA) measurements, taking into account that, for the same temperature and time, the weight loss of a bulk specimen is lower than for a powder TGA. The degraded specimens were then tested, and the shear strengths were reported vs. the weight loss.

**2.3 Processing.** The bulk AS4/3501-6 baseline material and the AS4/3501-6 with the cocured PSU film were processed in an autoclave, following the cure cycle given by the AS4/3501-6 supplier. No enhanced cycle was used for the parts with the PSU film. The bulk AS4/3501-6 baselines were composed of 24 plies (0°). The cocured parts composed 24 plies of the AS4/3501-6 baseline and 1 ply of 0.15 mm or 0.30-mm-thick PSU film on one side of the laminate.

The heating elements for the resistance welding were vacuum bag processed in the oven and were composed of 1 ply of carbon fiber/polyarylsulphone (CF/PASU) sandwiched between two layers of 0.15-mm-thick PSU film. In order to ensure a good electrical contact between the fibers and the electrical circuit, metal meshes were then ultrasonically welded at both ends of the composite heating elements (Figure 1).

**2.4 Welding.** The controlled parameters for the welding process were essentially the power, pressure, and dwell time. The power was set to 50 kW/m<sup>2</sup> for all welds. The pressure was set to 0.38 MPa and 0.17 MPa for the parts with the 0.15-mm- and 0.30-mm-thick cocured PSU layer, respectively. The temperatures and dwell times were set from 250 °C to 300 °C and from 45 s to 300 s, respectively, and were chosen case by case,


depending on the quality and shear strength value of the preceding weld. For the first weld, the parameters were chosen according to previous work [6], where CF/PASU was used instead of AS4/3501-6.

**2.5 Testing.** Two test methods were used in order to assess the shear strength of the degraded bulk AS4/3501-6 composite as well as the weld strengths. The first one was the apparent interlaminar shear strength test (ILSS) [7], used for the degradation assessment. Since this test was not efficient enough for the testing of the welds, the interlaminar shear device test (ISD) [8] was used for this purpose. Normalized to the nondegraded bulk AS4/3501-6, these two test methods gave identical results. In the following sections, only the normalized shear strengths (NSS) are compared. Test samples were cut out from several positions of the welded samples.

### 3. Results and Discussion

**3.1 Degradation.** As shown in Figure 2, the thermal degradation of the bulk AS4/3501-6 baseline is evidenced and reported to decrease the shear strength vs. the weight loss in an exponential way. The legend shows at which temperature and time the specimens were degraded. The two corresponding photographs illustrate the effect of the thermal degradation, which manifests by a weight loss, on the microstructure of the specimens having no weight loss and 7.5% weight loss, respectively.

For degraded composite, delamination between the plies is responsible for the very low shear strength. For the case of no weight loss, the scatter in shear strengths in Figure 2, is certainly due to a lower initial consolidation between the plies because a loss of vacuum pressure occurred during the curing in autoclave. On the other hand, for the 7.5% weight loss, there is an evident loss of resin between the plies, which is certainly due to changes in the chemical structure of the resin.



**Figure 2. Effect of Thermal Degradation on the Bulk AS4/3501-6 Baselines.**

It is also observed that the difference in terms of weight loss between TGA measurements and degradation in the oven decreases with exposure to increasing temperature. The measured bulk sample (oven) weight loss is consistently less than that determined by TGA measurements (Table 1).

**Table 1. Differences of Weight Losses Between TGA and Degradation in an Oven for Several Exposure Conditions.**

Temperature (°C)	Time (min)	TGA Weight Loss (%)	Oven Weight Loss (%)	Deviation (%)
250	55	1.0	0.39	61.0
300	10	1.5	1.20	20.0
300	16	2.0	1.37	31.5
300	28	3.0	2.28	24.0
320	25	5.0	3.05	39.0
345	60	8.0	7.69	3.9


Applying these results to the welding process, the thermal degradation of the AS4/3501-6 is expected to be negligible (2% or less) if welding occurs around 300 °C for a few minutes.

**3.2 Thermoset/Thermoplastic Bond Quality.** The quality of the bonds between the AS4/3501-6 and the PSU film is reported to be good because some 3501-6 resin diffused and even flowed through the whole thickness of the PSU film during autoclave cure. These parts are not used for welding because the surface to be welded is not pure PSU but a blend of both PSU and 3501-6 resin, which could alter the quality of the welded bond. In order to control an efficient diffusion of the 3501-6 monomers, an optimization of the cure cycle has to be studied.


**3.3 Welding Properties.** After several experiments to optimize the welding parameters, it is observed that the quality of the heating element and the contact of the welded metal meshes with the prepreg are very important in order to ensure reproducibility. The polymer flow at the edges can be reduced by lowering the pressure, and the local overheating can be minimized by adding two cooling nitrogen fluxes on the edges along the fiber direction.

Although the control of the welding process is not optimum and the reproducibility is not ideal, three different results are experienced. The first case is related to the welds with the highest NSS, which is obtained at a process temperature of 300 °C for 10 s (Figure 3). The average NSS is homogeneous in the plane of the weld interface, and the NSS is close to the bulk AS4/3501-6 shear strength (NSS = 1). It can be concluded that the interdiffusion of the PSU chains and the formation of IPN occurred with these welding parameters.

The second case is observed for welds that have an average NSS near 0.5 (Figure 4) and that are processed at 250 °C for 300 s. Again, the NSS is homogeneous in the plane of the weld interface; however, the shear strength is half that of the bulk AS4/3501-6. This is evidently not due to thermal degradation but to a low bond consolidation and incomplete interdiffusion of PSU at this lower temperature.




**Figure 3. Results of Two Typical Good-Quality Welds With a Shear Strength Close to the Bulk AS4/3501-6 Baseline. Bond Strengths Are Uniformly Distributed Across the Width of All Welded Areas.**




**Figure 4. Results of Four Typical Poor-Quality Welds at Low Consolidation Temperature.**

The third result represents the effect of the heat gradient across the weld. The edge along the fibers direction went up to 600 °C for 10 s (Figure 5), and the rest of the weld went to between 300 °C and 400 °C for 30 s. The NSS at the edge is low (due to degradation). The other NSS values are lower than unity. This is linked to a temperature above 300 °C for more than 10 s, which induces degradation. However, the locations of the highest NSS in Figure 5 are reported for temperatures around 300 °C. The three different behaviors (Figures 3–5) correlate quantitatively with the degradation results presented in Figure 2.




**Figure 5. Results of Four Typical Welds Evidencing the Inhomogeneity of Thermal History Influencing the Distribution of the Bond Strengths.**

Micrographs of the weld cross sections are presented as qualitative evidence of the degradation. As shown in Figures 6 and 7, the bond quality and, therefore, the NSS are completely different for a nondegraded and a degraded weld. The nondegraded weld contains no voids. The degraded weld shows degraded material and a high percentage of voids in regions close to the edges of the weld where the flow of the PSU is higher.



**Figure 6. Good-Quality Weld (NSS = 1).**



**Figure 7. Degraded Weld (NSS = 0.5).**

**3.4 Failure Mechanisms.** In most of the cases, the failure of the welds is cohesive within the composite elements of the complex joint structure. As shown in Figure 8, the failure propagates at the interface between AS4/3501-6 and PSU (TS/TP), crosses the PSU layers, and propagates at the interface between the PASU prepreg of the heating element (TP/h.e.) and the PSU. The two failure interfaces (top and bottom) are of a different nature. The top interface is the result of two mechanisms. First, an adhesive rupture around the fibers is evidenced by the cleanness of some of the fibers, and then a plastic deformation of the PSU is shown by the rough and ductile surface aspect of the PSU. The bottom interface is produced only by an adhesive rupture around the fibers.




Figure 8. Typical Mixed Failure of the Weld.

These results indicate a competition between the failures of the two interfaces. The bottom interface is weaker because less energy can be absorbed by plastic deformation. No failure is observed at the original PSU/PSU interface. These interfaces are not even visible in Figure 8 (dashed line), which indicates a good interdiffusion between the thermoplastics.

## 4. Conclusion

The feasibility of welding TP to TS is demonstrated in this work. The thermal degradation is shown to affect the shear properties of the TS by decreasing its shear strength exponentially. During welding, degradation is negligible if correct welding processing parameters are used. The diffusion of the 3501-6 resin into the cocured PSU layer is obtained without the use of an enhanced diffusion cycle. Nevertheless, the conditions need to be optimized in order to better control the diffusion length.

The selected welding parameters resulted in three different scenarios. The bonds with the higher shear strengths are processed at 300 °C for 10 s. Lower temperatures induce insufficient

molecular interdiffusion and weak consolidation. Last, excessive temperatures induce degradation. The failure of the welds is dominated more by composite interfaces (fibers/matrices) than by the interfaces between thermoplastic and thermoset polymers. Bonding of dissimilar materials such as thermoplastics and thermosets holds promise for assembly of complex composite structures.

## 5. References

1. Das, B., D. Chakraborty, A. K. Hajra, and S. Sinha. "Epoxy/Poly (methyl, methacrylate) Interpenetrating Polymer Networks—Morphology, Mechanical and Thermal Properties." *Journal of Applied Polymer Science*, vol. 53, pp. 1491–1496, 1994.
2. Don, R. C., S. H. McKnight, E. D. Wetzel, A. McIntire, and J. W. Gillespie, Jr. "Interpenetrating Polymer Networks of Polyurethane and Epoxy." *Journal of Materials Science*, vol. 29, pp. 5435–5440, 1994.
3. Don, R. C., J. W. Gillespie, Jr., and S. H. McKnight. "A Study of Improved Bonding Techniques for High Performance Thermoplastic Composites." *Advanced Composites X: Proceedings of the 10th Annual ASM/ESD Advanced Composites Conference*, Dearborn, MI, vol. 7, pp. 605–614, 10 November 1994.
4. Kukich, D. S., V. M. Karbhari, D. A. Steenkamer, and S. H. McKnight. "Center for Composite Materials." CCM 94-07, University of Delaware, Newark, DE, 1994.
5. Don, R. C., L. Bastien, T. B. Jakobsen, and J. W. Gillespie, Jr. "Fusion Bonding of Thermoplastic Composites by Resistance Heating." *SAMPE Journal*, January/February 1990.
6. Howie, I., J. W. Gillespie, Jr., and A. J. Smiley. CCM 93-17, *Center for Composite Materials*, University of Delaware, Newark, DE, 1993.
7. American Society for Testing and Materials. "Standard Test Method for Apparent Interlaminar Shear Strength of Parallel Fiber Composites by Short-Beam Method." *Annual Book of ASTM Standards*, ASTM D 2344-84, 1998.
8. Rosselli, F. Personal communication. University of Delaware, Newark, DE, 1995.

INTENTIONALLY LEFT BLANK.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218	1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AI R 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	HQDA DAMO FDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460	3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	OSD OUSD(A&T)/ODDR&E(R) DR R J TREW 3800 DEFENSE PENTAGON WASHINGTON DC 20301-3800	3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AP 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	COMMANDING GENERAL US ARMY MATERIEL CMD AMCRDA TF 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001		<u>ABERDEEN PROVING GROUND</u>
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316	2	DIR USARL AMSRL CI LP (BLDG 305)
1	DARPA SPECIAL PROJECTS OFFICE J CARLINI 3701 N FAIRFAX DR ARLINGTON VA 22203-1714		
1	US MILITARY ACADEMY MATH SCI CTR EXCELLENCE MADN MATH MAJ HUBER THAYER HALL WEST POINT NY 10996-1786		
1	DIRECTOR US ARMY RESEARCH LAB AMSRL D DR D SMITH 2800 POWDER MILL RD ADELPHI MD 20783-1197		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CP CA D SNIDER 2800 POWDER MILL RD ADELPHI MD 20783-1145	1	COMMANDER US ARMY ARDEC AMSTA AR M D DEMELLA PICATINNY ARSENAL NJ 07806-5000
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TA 2800 POWDER MILL RD ADELPHI MD 20783-1145	3	COMMANDER US ARMY ARDEC AMSTA AR FSA A WARNASH B MACHAK M CHIEFA PICATINNY ARSENAL NJ 07806-5000
3	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TL 2800 POWDER MILL RD ADELPHI MD 20783-1145	2	COMMANDER US ARMY ARDEC AMSTA AR FSP G M SCHIKSNIS D CARLUCCI PICATINNY ARSENAL NJ 07806-5000
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TP 2800 POWDER MILL RD ADELPHI MD 20783-1145	1	COMMANDER US ARMY ARDEC AMSTA AR FSP A P KISATSKY PICATINNY ARSENAL NJ 07806-5000
1	DIRECTOR DA OASARDA SARD SO 103 ARMY PENTAGON WASHINGTON DC 20310-0103	2	COMMANDER US ARMY ARDEC AMSTA AR CCH C H CHANIN S CHICO PICATINNY ARSENAL NJ 07806-5000
1	DPTY ASST SECY FOR R&T SARD TT THE PENTAGON RM 3EA79 WASHINGTON DC 20301-7100	1	COMMANDER US ARMY ARDEC AMSTA AR QAC T D RIGOGLIOSO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY MATERIEL CMD AMXMI INT 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001	1	COMMANDER US ARMY ARDEC AMSTA AR QAC T D RIGOGLIOSO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T C C PATEL PICATINNY ARSENAL NJ 07806-5000		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY ARDEC AMSTA AR SRE D YEE PICATINNY ARSENAL NJ 07806-5000	1	US ARMY ARDEC INTELLIGENCE SPECIALIST AMSTA AR WEL F M GUERRIERE PICATINNY ARSENAL NJ 07806-5000
9	COMMANDER US ARMY ARDEC AMSTA AR CCH B P DONADIA F DONLON P VALENTI C KNUTSON G EUSTICE S PATEL G WAGNECZ R SAYER F CHANG PICATINNY ARSENAL NJ 07806-5000	11	PM TMAS SFAE GSSC TMA R MORRIS C KIMKER D GUZOWICZ E KOPACZ R ROESER R DARCY R MCDANOLDS L D ULISSE C ROLLER J MCGREEN B PATTTER PICATINNY ARSENAL NJ 07806-5000
6	COMMANDER US ARMY ARDEC AMSTA AR CCL F PUZYCKI R MCHUGH D CONWAY E JAROSZEWSKI R SCHLENNER M CLUNE PICATINNY ARSENAL NJ 07806-5000	2	PEO FIELD ARTILLERY SYS SFAE FAS PM H GOLDMAN T MCWILLIAMS PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR WET T SACHAR BLDG 172 PICATINNY ARSENAL NJ 07806-5000	1	COMMANDER US ARMY ARDEC AMSTA AR WEA J BRESCIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA ASF PICATINNY ARSENAL NJ 07806-5000	1	COMMANDER US ARMY ARDEC PRODUCTION BASE MODERN ACTY AMSMC PBM K PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY TACOM PM ABRAMS SFAE ASM AB 6501 ELEVEN MILE RD WARREN MI 48397-5000
6	PM SADARM SFAE GCSS SD COL B ELLIS M DEVINE R KOWALSKI W DEMASSI J PRITCHARD S HROWNAK PICATINNY ARSENAL NJ 07806-5000
3	COMMANDER US ARMY TACOM PM TACTICAL VEHICLES SFAE TVL SFAE TVM SFAE TVH 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM BFVS SFAE ASM BV 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM AFAS SFAE ASM AF 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM RDT&E SFAE GCSS W AB J GODELL 6501 ELEVEN MILE RD WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMMANDER US ARMY TACOM PM SURV SYS SFAE ASM SS T DEAN SFAE GCSS W GSI M D COCHRAN 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM SURVIVABLE SYSTEMS SFAE GCSS W GSI H M RYZYI 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM BFV SFAE GCSS W BV S DAVIS 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM LIGHT TACTICAL VHCLS AMSTA TR S A J MILLS MS 209 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM GROUND SYSTEMS INTEGRATION SFAE GCSS W GSI R LABATILLE 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM CHIEF ABRAMS TESTING SFAE GCSS W AB QT T KRASKIEWICZ 6501 ELEVEN MILE RD WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY TACOM AMSTA SF WARREN MI 48397-5000	11	BENET LABORATORIES AMSTA AR CCB R FISCELLA G D ANDREA E KATHE M SCAVULO G SPENCER P WHEELER K MINER J VASILAKIS G FRIAR R HASENBEIN AMSTA CCB R S SOPOK WATERVLIET NY 12189-4050
1	COMMANDER WATERVLIET ARSENAL SMCWV QAE Q B VANINA BLDG 44 WATERVLIET NY 12189-4050		
15	COMMANDER US ARMY TACOM AMSTA TR R J CHAPIN R MCCLELLAND D THOMAS J BENNETT D HANSEN AMSTA JSK S GOODMAN J FLORENCE K IYER D TEMPLETON A SCHUMACHER AMSTA TR D D OSTBERG L HINOJOSA B RAJU AMSTA CS SF H HUTCHINSON F SCHWARZ WARREN MI 48397-5000	3	ARMOR SCHOOL ATZK TD R BAUEN J BERG A POMEY FT KNOX KY 40121
		2	HQ IOC TANK AMMUNITION TEAM AMSIO SMT R CRAWFORD W HARRIS ROCK ISLAND IL 61299-6000
		1	DIRECTOR US ARMY AMCOM SFAE AV RAM TV D CALDWELL BLDG 5300 REDSTONE ARSENAL AL 35898
1	COMMANDER WATERVLIET ARSENAL SMCWV SPM T MCCLOSKEY BLDG 253 WATERVLIET NY 12189-4050	2	COMMANDER US ARMY AMCOM AVIATION APPLIED TECH DIR J SCHUCK FT EUSTIS VA 23604-5577
2	TSM ABRAMS ATZK TS S JABURG W MEINSHAUSEN FT KNOX KY 40121	1	US ARMY CERL R LAMPO 2902 NEWMARK DR CHAMPAIGN IL 61822

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	AFRL F ABRAMS J BROWN BLDG 653 2977 P ST STE 6 WRIGHT PATTERSON AFB OH 45433-7739	1	FAA MIL HDBK 17 CHAIR L ILCEWICZ 1601 LIND AVE SW ANM 115N RESTON VA 98055
1	AFRL MLS OL L COULTER 7278 4TH ST BLDG 100 BAY D HILL AFB UT 84056-5205	1	US DEPT OF ENERGY OFC OF ENVIRONMENTAL MANAGEMENT P RITZCOVAN 19901 GERMANTOWN RD GERMANTOWN MD 20874-1928
1	OSD JOINT CCD TEST FORCE OSD JCCD R WILLIAMS 3909 HALLS FERRY RD VICKSBURG MS 29180-6199	1	DIRECTOR LLNL F ADDESSIO MS B216 PO BOX 1633 LOS ALAMOS NM 87545
1	DEFENSE NUCLEAR AGENCY INNOVATIVE CONCEPTS DIV 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398	5	DIRECTOR LLNL R CHRISTENSEN S DETERESA F MAGNESS M FINGER MS 313 M MURPHY L 282 PO BOX 808 LIVERMORE CA 94550
1	WATERWAYS EXPERIMENT D SCOTT 3909 HALLS FERRY RD SC C VICKSBURG MS 39180	1	OAK RIDGE NATIONAL LABORATORY R M DAVIS PO BOX 2008 OAK RIDGE TN 37831-6195
2	FAA TECH CENTER P SHYPRYKEVICH AAR 431 ATLANTIC CITY NJ 08405	1	OAK RIDGE NATIONAL LABORATORY C EBERLE MS 8048 PO BOX 2009 OAK RIDGE TN 37831
3	DARPA M VANFOSSEN S WAX L CHRISTODOULOU 3701 N FAIRFAX DR ARLINGTON VA 22203-1714	1	OAK RIDGE NATIONAL LABORATORY C D WARREN MS 8039 PO BOX 2009 OAK RIDGE TN 37922
2	SERDP PROGRAM OFC PM P2 C PELLERIN B SMITH 901 N STUART ST STE 303 ARLINGTON VA 22203		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
7	NIST R PARNAS J DUNKERS M VANLANDINGHAM MS 8621 J CHIN MS 8621 D HUNSTON MS 8543 J MARTIN MS 8621 D DUTHINH MS 8611 100 BUREAU DR GAITHERSBURG MD 20899	1	CENTRAL INTLLGNC AGENCY OTI WDAG GT W L WALTMAN PO BOX 1925 WASHINGTON DC 20505
1	HYDROGEOLOGIC INC SERDP ESTCP SPT OFC S WALSH 1155 HERNDON PKWY STE 900 HERNDON VA 20170	1	MARINE CORPS INTELLIGENCE ACTIVITY D KOSITZKE 3300 RUSSELL RD STE 250 QUANTICO VA 22134-5011
3	DIRECTOR SANDIA NATIONAL LABS APPLIED MECHANICS DEPT DIV 8241 J HANDROCK Y R KAN J LAUFFER PO BOX 969 LIVERMORE CA 94550-0096	1	DIRECTOR NATIONAL GRND INTLLGNC CTR IANG TMT 220 SEVENTH ST NE CHARLOTTESVILLE VA 22902-5396
3	NASA LANGLEY RSCH CTR AMSRL VS W ELBER MS 266 F BARTLETT JR MS 266 G FARLEY MS 266 HAMPTON VA 23681-0001	1	DIRECTOR DEFENSE INTLLGNC AGENCY TA 5 K CRELLING WASHINGTON DC 20310
1	NASA LANGLEY RSCH CTR T GATES MS 188E HAMPTON VA 23661-3400	1	GRAPHITE MASTERS INC J WILLIS 3815 MEDFORD ST LOS ANGELES CA 90063-1900
1	USDOT FEDERAL RAILRD M FATEH RDV 31 WASHINGTON DC 20590	1	ADVANCED GLASS FIBER YARNS T COLLINS 281 SPRING RUN LANE STE A DOWNINGTON PA 19335
1	FHWA E MUNLEY 6300 GEORGETOWN PIKE MCLEAN VA 22101	1	COMPOSITE MATERIALS INC D SHORTT 19105 63 AVE NE PO BOX 25 ARLINGTON WA 98223
		1	COMPOSITE MATERIALS INC R HOLLAND 11 JEWEL CT ORINDA CA 94563
		1	COMPOSITE MATERIALS INC C RILEY 14530 S ANSON AVE SANTA FE SPRINGS CA 90670

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMPOSIX D BLAKE L DIXON 120 O NEILL DR HEBRUN OHIO 43025	2	TEXTRON SYSTEMS T FOLTZ M TREASURE 201 LOWELL ST WILMINGTON MA 08870-2941
4	CYTEC FIBERITE R DUNNE D KOHLI M GILLIO R MAYHEW 1300 REVOLUTION ST HAVRE DE GRACE MD 21078	1	JPS GLASS L CARTER PO BOX 260 SLATER RD SLATER SC 29683
2	SIMULA J COLTMAN R HUYETT 10016 S 51ST ST PHOENIX AZ 85044	2	MILLIKEN RSCH CORP H KUHN M MACLEOD PO BOX 1926 SPARTANBURG SC 29303
1	SIOUX MFG B KRIEL PO BOX 400 FT TOTTEN ND 58335	1	CONNEAUGHT INDUSTRIES INC J SANTOS PO BOX 1425 COVENTRY RI 02816
2	PROTECTION MATERIALS INC M MILLER F CRILLEY 14000 NW 58 CT MIAMI LAKES FL 33014	2	BATTELLE NATICK OPNS J CONNORS B HALPIN 209 W CENTRAL ST STE 302 NATICK MA 01760
3	FOSTER MILLER J J GASSNER M ROYLANCE W ZUKAS 195 BEAR HILL RD WALTHAM MA 02354-1196	1	ARMTEC DEFENSE PRODUCTS S DYER 85 901 AVE 53 PO BOX 848 COACHELLA CA 92236
1	ROM DEVELOPMENT CORP R O MEARA 136 SWINEBURNE ROW BRICK MARKET PLACE NEWPORT RI 02840	1	GLCC INC J RAY 103 TRADE ZONE DR STE 26C WEST COLUMBIA SC 29170
1	O GARA HESS & EISENHARDT M GILLESPIE 9113 LESAINTE DR FAIRFIELD OH 45014	3	PACIFIC NORTHWEST LAB M SMITH G VAN ARSDALE R SHIPPELL PO BOX 999 RICHLAND WA 99352

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	AMOCO PERFORMANCE PRODUCTS M MICHNO JR J BANISAUKAS 4500 MCGINNIS FERRY RD ALPHARETTA GA 30202-3944	1	PROJECTILE TECHNOLOGY INC 515 GILES ST HAVRE DE GRACE MD 21078
1	SAIC M PALMER 1410 SPRING HILL RD STE 400 MS SH4 5 MCLEAN VA 22102	1	LORAL VOUGHT SYSTEMS K COOK 1701 W MARSHALL DR GRAND PRAIRIE TX 75051
1	SAIC G CHRYSSOMALLIS 3800 W 80TH ST STE 1090 BLOOMINGTON MN 55431	3	HEXCEL INC R BOE PO BOX 18748 SALT LAKE CITY UT 84118
1	AAI CORPORATION T G STASTNY PO BOX 126 HUNT VALLEY MD 21030-0126	8	ALLIANT TECHSYSTEMS INC C CANDLAND MN11 2830 C AAKHUS MN11 2830 B SEE MN11 2439 N VLAHAKUS MN11 2145 R DOHRN MN11 2830 S HAGLUND MN11 2439 M HISSONG MN11 2830 D KAMDAR MN11 2830 600 SECOND ST NE HOPKINS MN 55343-8367
1	APPLIED COMPOSITES W GRISCH 333 NORTH SIXTH ST ST CHARLES IL 60174	5	AEROJET GEN CORP D PILLASCH T COULTER C FLYNN D RUBAREZUL M GREINER 1100 WEST HOLLYVALE ST AZUSA CA 91702-0296
3	ALLIANT TECHSYSTEMS INC J CONDON E LYNAM J GERHARD WV01 16 STATE RT 956 PO BOX 210 ROCKET CENTER WV 26726-0210	1	HERCULES INC HERCULES PLAZA WILMINGTON DE 19894
1	CUSTOM ANALYTICAL ENG SYS INC A ALEXANDER 13000 TENSOR LANE NE FLINTSTONE MD 21530	1	BRIGS COMPANY J BACKOFEN 2668 PETERBOROUGH ST HERNDON VA 22071-2443
1	OFC DEPUTY UNDER SEC DFNS J THOMPSON 1745 JEFFERSON DAVIS HWY CRYSTAL SQ 4 STE 501 ARLINGTON VA 22202	1	ZERNOW TECHNICAL SERVICES L ZERNOW 425 W BONITA AVE STE 208 SAN DIMAS CA 91773

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	OLIN CORPORATION FLINCHBAUGH DIV E STEINER B STEWART PO BOX 127 RED LION PA 17356	1	BOEING R BOHLMANN PO BOX 516 MC 5021322 ST LOUIS MO 63166-0516
1	OLIN CORPORATION L WHITMORE 10101 NINTH ST NORTH ST PETERSBURG FL 33702	2	BOEING DFNSE & SPACE GP W HAMMOND S 4X55 J RUSSELL S 4X55 PO BOX 3707 SEATTLE WA 98124-2207
1	GKN AEROSPACE D OLDS 15 STERLING DR WALLINGFORD CT 06492	2	BOEING ROTORCRAFT P MINGURT P HANDEL 800 B PUTNAM BLVD WALLINGFORD PA 19086
1	PRATT & WHITNEY C WATSON 400 MAIN ST MS 114 37 EAST HARTFORD CT 06108	1	BOEING DOUGLAS PRODUCTS DIV L J HART SMITH 3855 LAKEWOOD BLVD D800 0019 LONG BEACH CA 90846-0001
5	SIKORSKY AIRCRAFT G JACARUSO T CARSTENSAN B KAY S GARBO MS S330A J ADELMANN 6900 MAIN ST PO BOX 9729 STRATFORD CT 06497-9729	1	LOCKHEED MARTIN S REEVE 8650 COBB DR D 73 62 MZ 0648 MARIETTA GA 30063-0648
1	AEROSPACE CORP G HAWKINS M4 945 2350 E EL SEGUNDO BLVD EL SEGUNDO CA 90245	1	LOCKHEED MARTIN SKUNK WORKS D FORTNEY 1011 LOCKHEED WAY PALMDALE CA 93599-2502
2	CYTEC FIBERITE M LIN W WEB 1440 N KRAEMER BLVD ANAHEIM CA 92806	1	LOCKHEED MARTIN R FIELDS 1195 IRWIN CT WINTER SPRINGS FL 32708
1	HEXCEL T BITZER 11711 DUBLIN BLVD DUBLIN CA 94568	1	MATERIALS SCIENCES CORP B W ROSEN 500 OFC CENTER DR STE 250 FT WASHINGTON PA 19034

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	NORTHROP GRUMMAN CORP ELECTRONIC SENSORS & SYSTEMS DIV E SCHOCH MS V 16 1745A W NURSERY RD LINTHICUM MD 21090
2	NORTHROP GRUMMAN ENVIRONMENTAL PROGRAMS R OSTERMAN A YEN 8900 E WASHINGTON BLVD PICO RIVERA CA 90660
1	UDLP D MARTIN PO BOX 359 SANTA CLARA CA 95052
1	UDLP G THOMAS PO BOX 58123 SANTA CLARA CA 95052
2	UDLP R BARRETT MAIL DROP M53 V HORVATICH MAIL DROP M53 328 W BROKAW RD SANTA CLARA CA 95052-0359
3	UDLP GROUND SYSTEMS DIVISION M PEDRAZZI MAIL DROP N09 A LEE MAIL DROP N11 M MACLEAN MAIL DROP N06 1205 COLEMAN AVE SANTA CLARA CA 95052
4	UDLP R BRYNSVOLD P JANKE MS 170 4800 EAST RIVER RD MINNEAPOLIS MN 55421-1498
1	GDLS DIVISION D BARTLE PO BOX 1901 WARREN MI 48090

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	GDLS D REES M PASIK PO BOX 2074 WARREN MI 48090-2074
1	GDLS MUSKEGON OPERATIONS W SOMMERS JR 76 GETTY ST MUSKEGON MI 49442
1	GENERAL DYNAMICS AMPHIBIOUS SYS SURVIVABILITY LEAD G WALKER 991 ANNAPOLIS WAY WOODBIDGE VA 22191
6	INST FOR ADVANCED TECH H FAIR I MCNAB P SULLIVAN S BLESS W REINECKE C PERSAD 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
2	CIVIL ENGR RSCH FOUNDATION PRESIDENT H BERNSTEIN R BELLE 1015 15TH ST NW STE 600 WASHINGTON DC 20005
1	ARROW TECH ASSOC 1233 SHELBURNE RD STE D 8 SOUTH BURLINGTON VT 05403-7700
1	R EICHELBERGER CONSULTANT 409 W CATHERINE ST BEL AIR MD 21014-3613
1	UCLA MANE DEPT ENGR IV H T HAHN LOS ANGELES CA 90024-1597

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	UNIV OF DAYTON RESEARCH INST R Y KIM A K ROY 300 COLLEGE PARK AVE DAYTON OH 45469-0168
1	MIT P LAGACE 77 MASS AVE CAMBRIDGE MA 01887
1	IIT RESEARCH CENTER D ROSE 201 MILL ST ROME NY 13440-6916
1	GA TECH RSCH INST GA INST OF TCHNLGY P FRIEDERICH ATLANTA GA 30392
1	MICHIGAN ST UNIV MSM DEPT R AVERILL 3515 EB EAST LANSING MI 48824-1226
1	UNIV OF KENTUCKY L PENN 763 ANDERSON HALL LEXINGTON KY 40506-0046
1	UNIV OF WYOMING D ADAMS PO BOX 3295 LARAMIE WY 82071
2	PENN STATE UNIV R MCNITT C BAKIS 212 EARTH ENGR SCIENCES BLDG UNIVERSITY PARK PA 16802
1	PENN STATE UNIV R S ENGEL 245 HAMMOND BLDG UNIVERSITY PARK PA 16801

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	PURDUE UNIV SCHOOL OF AERO & ASTRO C T SUN W LAFAYETTE IN 47907-1282
1	STANFORD UNIV DEPT OF AERONAUTICS & AEROBALLISTICS S TSAI DURANT BLDG STANFORD CA 94305
1	UNIV OF DAYTON J M WHITNEY COLLEGE PARK AVE DAYTON OH 45469-0240
7	UNIV OF DELAWARE CTR FOR COMPOSITE MTRLS J GILLESPIE M SANTARE G PALMESE S YARLAGADDA S ADVANI D HEIDER D KUKICH 201 SPENCER LABORATORY NEWARK DE 19716
1	DEPT OF MATERIALS SCIENCE & ENGINEERING UNIVERSITY OF ILLINOIS AT URBANA CHAMPAIGN J ECONOMY 1304 WEST GREEN ST 115B URBANA IL 61801
1	NORTH CAROLINA STATE UNIV CIVIL ENGINEERING DEPT W RASDORF PO BOX 7908 RALEIGH NC 27696-7908
3	THE UNIV OF TEXAS AT AUSTIN CTR FOR ELECTROMECHANICS J PRICE A WALLS J KITZMILLER 10100 BURNET RD AUSTIN TX 78758-4497

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	VA POLYTECHNICAL INST & STATE UNIV DEPT OF ESM M W HYER K REIFSNIDER R JONES BLACKSBURG VA 24061-0219
1	UNIV OF MARYLAND DEPT OF AEROSPACE ENGNRNG A J VIZZINI COLLEGE PARK MD 20742
1	DREXEL UNIV A S D WANG 32ND & CHESTNUT ST PHILADELPHIA PA 19104
1	SOUTHWEST RSCH INST ENGR & MATL SCIENCES DIV J RIEGEL 6220 CULEBRA RD PO DRAWER 28510 SAN ANTONIO TX 78228-0510

ABERDEEN PROVING GROUND

1	US ARMY MATERIEL SYSTEMS ANALYSIS P DIETZ 392 HOPKINS RD AMXSY TD APG MD 21005-5071
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP AP L APG MD 21005-5066
105	DIR USARL AMSRL CI AMSRL CI H W STUREK AMSRL CI S A MARK AMSRL CS IO FI M ADAMSON AMSRL SL B J SMITH

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
	<u>ABERDEEN PROVING GROUND (CONT)</u>
	AMSRL SL BA AMSRL SL BL D BELY R HENRY AMSRL SL BG AMSRL SL I AMSRL WM B A HORST E SCHMIDT AMSRL WM BA F BRANDON AMSRL WM BC P PLOSTINS D LYON J NEWILL S WILKERSON A ZIELINSKI AMSRL WM BD B FORCH R FIFER R PESCE RODRIGUEZ B RICE AMSRL WM BE C LEVERITT D KOOKER AMSRL WM BR C SHOEMAKER J BORNSTEIN AMSRL WM M D VIECHNICKI G HAGNAUER J MCCAULEY B TANNER AMSRL WM MA R SHUFORD P TOUCHET N BECK TAN AMSRL WM MA D FLANAGAN L GHIORSE D HARRIS S MCKNIGHT P MOY P PATTERSON G RODRIGUEZ A TEETS R YIN

NO. OF  
COPIES    ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM MB  
B FINK  
J BENDER  
T BOGETTI  
R BOSSOLI  
L BURTON  
K BOYD  
S CORNELISON  
P DEHMER  
R DOOLEY  
W DRYSDALE  
G GAZONAS  
S GHIORSE  
D GRANVILLE  
D HOPKINS  
C HOPPEL  
D HENRY  
R KASTE  
M KLUSEWITZ  
M LEADORE  
R LIEB  
E RIGAS  
J SANDS  
D SPAGNUOLO  
W SPURGEON  
J TZENG  
E WETZEL  
AMSRL WM MB  
A FRYDMAN  
AMRSL WM MC  
J BEATTY  
E CHIN  
J MONTGOMERY  
A WERECZCAK  
J LASALVIA  
J WELLS  
AMSRL WM MD  
W ROY  
S WALSH  
AMSRL WM T  
B BURNS  
AMSRL WM TA  
W GILLICH  
T HAVEL  
J RUNYEON  
M BURKINS  
E HORWATH  
B GOOCH  
W BRUCHEY

NO. OF  
COPIES    ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM TC  
R COATES  
AMSRL WM TD  
A DAS GUPTA  
T HADUCH  
T MOYNIHAN  
F GREGORY  
A RAJENDRAN  
M RAFTENBERG  
M BOTELER  
T WEERASOORIYA  
D DANDEKAR  
A DIETRICH  
AMSRL WM TE  
A NILER  
J POWELL  
AMSRL SS SD  
H WALLACE  
AMSRL SS SE R  
R CHASE  
AMSRL SS SE DS  
R REYZER  
R ATKINSON  
AMSRL SE L  
R WEINRAUB  
J DESMOND  
D WOODBURY

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	LTD R MARTIN MERL TAMWORTH RD HERTFORD SG13 7DG UK	1	ECOLE POLYTECH J MANSON DMX LTC CH 1015 LAUSANNE SWITZERLAND
1	SMC SCOTLAND P W LAY DERA ROSYTH ROSYTH ROYAL DOCKYARD DUNFERMLINE FIFE KY 11 2XR UK	1	SWISS FEDERAL ARMAMENTS WKS W LANZ ALLMENDSTRASSE 86 3602 THUN SWITZERLAND
1	CIVIL AVIATION ADMINSTRATION T GOTTESMAN PO BOX 8 BEN GURION INTERNL AIRPORT LOD 70150 ISRAEL	1	ISRAEL INST OF TECHNOLOGY S BODNER FACULTY OF MECHANICAL ENGR HAIFA 3200 ISRAEL
1	AEROSPATIALE S ANDRE A BTE CC RTE MD132 316 ROUTE DE BAYONNE TOULOUSE 31060 FRANCE	1	DSTO MATERIALS RESEARCH LAB NAVAL PLATFORM VULNERABILITY SHIP STRUCTURES & MTRLS DIV N BURMAN PO BOX 50 ASCOT VALE VICTORIA AUSTRALIA 3032
3	DRA FORT HALSTEAD P N JONES M HINTON SEVEN OAKS KENT TN 147BP UK	1	ECOLE ROYAL MILITAIRE E CELENS AVE DE LA RENAISSANCE 30 1040 BRUXELLE BELGIQUE
1	DEFENSE RESEARCH ESTAB VALCARTIER F LESAGE COURCELETTE QUEBEC COA IRO CANADA	1	DEF RES ESTABLISHMENT VALCARTIER A DUPUIS 2459 BOULEVARD PIE XI NORTH VALCARTIER QUEBEC CANADA PO BOX 8800 COURCELETTE GOA IRO QUEBEC CANADA
2	ROYAL MILITARY COLLEGE OF SCIENCE SHRIVENHAM D BULMAN B LAWTON SWINDON WILTS SN6 8LA UK		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	INSTITUT FRANCO ALLEMAND DE RECHERCHES DE SAINT LOUIS DE M GIRAUD 5 RUE DU GENERAL CASSAGNOU BOITE POSTALE 34 F 68301 SAINT LOUIS CEDEX FRANCE
1	TNO DEFENSE RESEARCH I H PASMEN POSTBUS 6006 2600 JA DELFT THE NETHERLANDS
1	TNO PRINS MAURITS LABORATORY R IJSELSTEIN LANGE KLEIWEG 137 PO BOX 45 2280 AA RIJSWIJK THE NETHERLANDS
2	FOA NATL DEFENSE RESEARCH ESTAB DIR DEPT OF WEAPONS & PROTECTION B JANZON R HOLMLIN S 172 90 STOCKHOLM SWEDEN
2	DEFENSE TECH & PROC AGENCY GROUND I CREWETHER GENERAL HERZOG HAUS 3602 THUN SWITZERLAND
1	MINISTRY OF DEFENCE RAFAEL ARMAMENT DEVELOPMENT AUTH M MAYSELESS PO BOX 2250 HAIFA 31021 ISRAEL

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DYNAMEC RESEARCH AB AKE PERSSON BOX 201 SE 151 23 SODERTALJE SWEDEN
1	B HIRSCH TACHKEMONY ST 6 NETAMUA 42611 ISRAEL
1	DEUTSCHE AEROSPACE AG DYNAMICS SYSTEMS M HELD PO BOX 1340 D 86523 SCHROBENHAUSEN GERMANY

# REPORT DOCUMENTATION PAGE

*Form Approved*  
*OMB No. 0704-0188*

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA, 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE May 2001	3. REPORT TYPE AND DATES COVERED Final, September 1995 - September 1996	
4. TITLE AND SUBTITLE Processing and Characterization of Welded Bonds Between Thermoset and Thermoplastic Composites		5. FUNDING NUMBERS 61105AH42	
6. AUTHOR(S) Stephen H. McKnight, Bruce K. Fink, Veronique Monnard,* P.-E. Bourban,* Jan-Anders E. Manson,* Douglas E. Eckel, II, <sup>†</sup> and John W. Gillespie, Jr. <sup>†</sup>			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-MA Aberdeen Proving Ground, MD 21005-5069		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-2484	
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES * Composite and Polymer Technology Laboratory, Swiss Federal Institute of Technology, CH 1015 Lausanne, Switzerland <sup>†</sup> University of Delaware, Newark, DE 19716			
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) <p>To assemble complex structures with short cycle times, the feasibility of welding thermoplastic (TP) to thermoset (TS) composites is demonstrated using a phenomenological approach. The effect of the thermal degradation of the TS composite (AS4/3501-6) on its shear strength is assessed in order to minimize the TS degradation during the welding process. The degradation is reported to decrease the shear strength in an exponential way. A layer of TP (polysulphone [PSU]) is cocured at the surface of the AS4/3501-6 laminate during its cure cycle in an autoclave. Two laminates are then welded together using a resistance welder. The highest shear strengths, which are close to the shear strength of bulk AS4/3501-6 autoclave-processed baseline, occur for a welding time and temperature of 10 s and 300 °C, respectively. Higher and lower temperatures induce degradation and low consolidation of the weld, respectively. The welding interface between the TP layers is the strongest, while failure is mixed and occurs at interfaces between TS and TP and at interfaces between TP and heating element at the fiber/matrix interfaces. Further investigations are required to optimize the welding processing parameters and to identify the bonding, degradation, and failure mechanisms using a more fundamental and molecular approach.</p>			
14. SUBJECT TERMS diffusion enhanced adhesion, composite, thermoset, thermoplastic		15. NUMBER OF PAGES 37	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL

INTENTIONALLY LEFT BLANK.

## USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2484 (McKnight) Date of Report May 2001

2. Date Report Received \_\_\_\_\_

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) \_\_\_\_\_

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) \_\_\_\_\_

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. \_\_\_\_\_

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) \_\_\_\_\_

CURRENT  
ADDRESS

\_\_\_\_\_  
Organization

\_\_\_\_\_  
Name

\_\_\_\_\_  
E-mail Name

\_\_\_\_\_  
Street or P.O. Box No.

\_\_\_\_\_  
City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD  
ADDRESS

\_\_\_\_\_  
Organization

\_\_\_\_\_  
Name

\_\_\_\_\_  
Street or P.O. Box No.

\_\_\_\_\_  
City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)  
**(DO NOT STAPLE)**

---


DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

**BUSINESS REPLY MAIL**  
FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR  
US ARMY RESEARCH LABORATORY  
ATTN AMSRL WM MA  
ABERDEEN PROVING GROUND MD 21005-5069



NO POSTAGE  
NECESSARY  
IF MAILED  
IN THE  
UNITED STATES

