



**Synthesis, Elemental Analysis, and Metallographic
Preparation of Lithium (Li)-Silicon (Si) Alloys**

**by Joshua B. Ratchford, Bruce A. Poese, Cynthia A. Lundgren, Jan L. Allen,
and Jeff Wolfenstine**

ARL-TR-5818

November 2011

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Adelphi, MD 20783-1197

ARL-TR-5818

November 2011

Synthesis, Elemental Analysis, and Metallographic Preparation of Lithium (Li)-Silicon (Si) Alloys

**Joshua B. Ratchford, Bruce A. Poes, Cynthia A. Lundgren, Jan L. Allen,
and Jeff Wolfenstine**

Sensors and Electron Devices Directorate, ARL

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) November 2011		2. REPORT TYPE Final		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Synthesis, Elemental Analysis, and Metallographic Preparation of Lithium (Li)-Silicon (Si) Alloys				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Joshua B. Ratchford, Bruce A. Poese, Cynthia A. Lundgren, Jan L. Allen, and Jeff Wolfenstine				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: RDRL-SED-C 2800 Powder Mill Road Adelphi, MD 20783-1197				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-5818	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT We report methods used to synthesize and prepare Li ₁₂ Si ₇ and Li ₂₂ Si ₅ for nanoindentation testing. The alloys were made by heating lithium granules with silicon powder. X-ray diffraction, inductively coupled plasma-mass spectrometry, and optical microscopy confirmed that the alloys were single phase. Optical microscopy showed that the alloys were fully dense.					
15. SUBJECT TERMS Lithium, silicon, alloys, synthesis					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 16	19a. NAME OF RESPONSIBLE PERSON Jeff Wolfenstine
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) (301) 394-0317

Contents

List of Figures	iv
List of Tables	iv
Acknowledgments	v
1. Introduction	1
2. Experimental	1
2.1 Synthesis.....	1
2.2 X-ray Diffraction Parameters	2
2.3 Inductively Coupled Plasma-Mass Spectrometry (ICP-MS)	2
2.4 Metallographic Preparation of Alloys	2
3. Results and Discussion	3
3.1 Phase Composition of Synthesized Alloys.....	3
3.2 Elemental Analysis.....	4
3.3 Microstructural Analysis	4
4. Conclusion	5
5. References	6
Distribution List	7

List of Figures

Figure 1. X-ray diffraction patterns produced from powder samples of (a) $\text{Li}_{12}\text{Si}_7$ and (b) $\text{Li}_{22}\text{Si}_5$	3
Figure 2. Optical images of etched samples (a) $\text{Li}_{12}\text{Si}_7$ and (b) $\text{Li}_{22}\text{Si}_5$	5

List of Tables

Table 1. Elemental composition of $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ determined by ICP-MS.	4
--	---

Acknowledgments

This research was performed while Joshua B. Ratchford held a National Research Council Research Associateship Award at the U.S. Army Research Laboratory. We are grateful to Dr. Matthew Ervin for the facilities used to polish samples.

INTENTIONALLY LEFT BLANK.

1. Introduction

Recently, lithium (Li)-silicon (Si) alloy anodes have been considered as attractive alternatives to graphite anodes in Li-ion batteries, because the specific capacities of these alloys are from four (1620 mAhg^{-1} , $\text{Li}_{12}\text{Si}_7$) to 10 times (4200 mAhg^{-1} , $\text{Li}_{22}\text{Si}_5$) greater than graphite (1–4). Unfortunately, these capacities diminish with cycling because substantial volume changes during Li-ion addition/removal cause decrepitation. It has been proposed that knowledge of the elastic properties of these alloys, like Young’s modulus, can be used to develop models that can predict and prevent decrepitation of Li-Si alloys (5, 6). Several groups recently predicted values of the elastic properties of these alloys using density functional theory (5, 7, 8). Experimental data to verify these values did not exist until our group’s recent publication of Young’s modulus for $\text{Li}_{22}\text{Si}_5$ that was measured using nanoindentation testing (9). We have also recently measured Young’s modulus for $\text{Li}_{12}\text{Si}_7$ using the same methods (10). We believe that the methods used for our work with $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ will be helpful to other researchers who wish to synthesize, study the microstructure, and measure the mechanical properties of Li alloys using nanoindentation testing. Therefore, the objective of this report is to document (1) the method used to synthesize $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$, (2) the methods we used to determine the weight percent of lithium of these alloys using inductively coupled plasma mass spectrometry (ICP-MS), and (3) the metallographic methods we used to prepare the surfaces of these alloys for microstructural analysis and nanoindentation testing.

2. Experimental

2.1 Synthesis

All procedures used to synthesize $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ were performed in a glove box (VAC Nexus One®) filled with argon, which contained less than 1 ppm of oxygen and 1 ppm of water. In order to synthesize $\text{Li}_{12}\text{Si}_7$, 1.490 g of lithium granules (Alfa Aesar) was mixed with 3.510 g of silicon powder (Alfa Aesar). In order to synthesize $\text{Li}_{22}\text{Si}_5$, 2.605 g of lithium granules were mixed with 2.395 g of silicon powder. The mixtures of the Li granules and Si powder were pressed into pellets using stainless steel dies. The pellets were heated inside molybdenum crucibles using a muffle furnace. The Li-Si phase diagram shows that $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ melt at $690 \text{ }^\circ\text{C}$ ($T_m = 963 \text{ K}$) (11). We found that samples heated to $800 \text{ }^\circ\text{C}$ showed improved phase purity as compared to those heated at $690 \text{ }^\circ\text{C}$. Therefore, the samples were heated from 20 to $800 \text{ }^\circ\text{C}$ over the course of 40 min and then at $800 \text{ }^\circ\text{C}$ for an additional 30 min. The samples were then heated at $450 \text{ }^\circ\text{C}$ for 16 h to ensure their homogeneity before it was slowly cooled to $20 \text{ }^\circ\text{C}$.

2.2 X-ray Diffraction Parameters

To determine the phase purity of $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$, approximately 100 mg of the samples were removed from the center of the crucibles, ground into fine powders, and placed upon a glass slides for analysis by x-ray diffraction. Because these alloys are sensitive to ambient moisture, the samples were hermetically sealed with Kapton® film before these were immediately transferred from the dry box to the x-ray diffractometer (Rigaku Ultima III®). A Cu-K α emission source and the Bragg-Brentano geometry was used to obtain a diffraction pattern from 15° to 80° two-theta with a step size of 0.02° two-theta at a scan rate of 1° two-theta per minute.

2.3 Inductively Coupled Plasma-Mass Spectrometry (ICP-MS)

Inductively coupled plasma-mass spectrometry (PerkinElmer ELAN® ICP-MS) was used to confirm the weight percentage of lithium in the alloys. For $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$, 100-mg powder samples were dissolved in solutions composed of 6 ml of 50 wt.% hydrofluoric acid (Fisher) and 3 ml of 70 wt.% nitric acid (Fisher) for 12 h in a Teflon® container. We wish to emphasize that extra caution was used to prepare these samples for ICP-MS because both alloys are very reactive with water. The sample solutions were then diluted to 100 g with a solution composed of 0.1 wt.% nitric acid and 0.3 wt.% hydrofluoric acid. $^7\text{Li}^+$ detection with the spectrometer was standardized with solutions made by diluting a 10- $\mu\text{g}/\text{ml}$ atomic absorption standard solution with a 0.1 wt.% nitric acid and 0.3 wt.% hydrofluoric acid solution at 10, 100, and 1000 times. Linear regression analysis of the $^7\text{Li}^+$ intensities measured from these standard solutions were used to generate the following calibration curve:

$$I_{\text{Li}} = 92.4 \times 10^3 C_{\text{Li}} + 4.0 \times 10^3 \quad (1)$$

where I_{Li} is the measured intensity of $^7\text{Li}^+$ and C_{Li} is the concentration of lithium in solution. $^7\text{Li}^+$ detection with the spectrometer was linear over four orders of magnitude. The measured intensity of $^7\text{Li}^+$ in the sample solution was substituted into equation 1 to determine the concentration of lithium, C_{Li} , in the dissolved $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ sample solutions.

2.4 Metallographic Preparation of Alloys

To prepare samples of $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ for mechanical testing, granules of the samples were cold mounted in epoxy (Buehler EPO-KWICK®)*. Granules were rough polished with 320-, 400-, and 600-grit abrasive papers (Buehler BuehlerMet®II) in series. Because the alloy is water reactive, the papers were lubricated with mineral oil instead of water. Suspensions of alumina powders (Buehler) in mineral oil were used to fine polish the granules against a microfiber cloth (Buehler MicroCloth® PSA). Alumina powders with diameters of 1.0, 0.3, and 0.05 μm were used in series. The surfaces of the granules were fine polished until a mirror finish was obtained. The homogeneity of the fine polished surface was confirmed by examination with optical microscopy. To determine the grain size of the alloy, the polished surfaces were etched for

* A stainless steel washer was used to hold the granules against the bottom surface of the mold as the liquid epoxy hardened.

several seconds with a solution that was 0.2% by mass water and 0.3% by mass hydrochloric acid diluted with hexane. Etching was quenched by immersing the sample into mineral oil. The grain size was measured from optical images of the etched surface using the linear intercept method (12).

3. Results and Discussion

3.1 Phase Composition of Synthesized Alloys

The x-ray diffraction patterns in figure 1a for $\text{Li}_{12}\text{Si}_7$ and figure 1b for $\text{Li}_{22}\text{Si}_5$ show that the alloys are polycrystalline. The amorphous background in the 15–30° range of figure 1b is an artifact of the Kapton tape. The position of the diffraction peaks that match those from the International Centre of Diffraction Data’s powder diffraction file for $\text{Li}_{12}\text{Si}_7$ (PDF# 00-040-0942) and $\text{Li}_{22}\text{Si}_5$ (PDF# 01-073-2049) are marked with bullets. Figure 1 shows that the positions of the diffraction peaks from the alloys agree perfectly with those from the powder diffraction files. Impurity peaks are marked with crossbars in figure 1a. These correspond to the (311) diffraction peak of Mo_4O_{11} (PDF# 01-089-6725) and the (111) diffraction peak of MoSi_2 (PDF# 01-081-0167). These results suggest that the synthesized $\text{Li}_{12}\text{Si}_7$ is mainly single phase $\text{Li}_{12}\text{Si}_7$ with a small amount of second phase Mo_4O_{11} and MoSi_2 impurities. No impurity peaks are observed in figure 1b. These results suggest that the synthesized $\text{Li}_{22}\text{Si}_5$ alloy is single phase $\text{Li}_{22}\text{Si}_5$.




Figure 1. X-ray diffraction patterns produced from powder samples of (a) $\text{Li}_{12}\text{Si}_7$ and (b) $\text{Li}_{22}\text{Si}_5$.

3.2 Elemental Analysis

Table 1 shows the measured weight percentages of lithium in the $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ obtained using ICP-MS, and the expected weight percentage of lithium in these alloys from the Li-Si phase diagram. As table 1 shows, the measured weight percentage of lithium in the alloys agrees with the expected weight percentage of lithium from the Li-Si phase diagram. These results further confirm that the synthesized alloys are indeed single phase $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$. Because molybdenum impurities were observed in the x-ray diffraction patterns obtained from the $\text{Li}_{12}\text{Si}_7$ samples, the weight percentage of molybdenum in this alloy was also measured. Table 1 shows that the weight percentage of molybdenum in this alloys was 1.8 ± 0.5 wt.%. In the worst case, the alloy is 2.3% by mass molybdenum. From this mass composition in conjunction with the densities of the impurities, the $\text{Li}_{12}\text{Si}_7$ alloy is at most 0.4 % .vol MoSi_2 or 0.5 % .vol Mo_4O_{11} —a negligible volume fraction to consider for a weighted average of mechanical properties for mixed phases of materials. From this result, we conclude that the mechanical properties measured from the synthesized $\text{Li}_{12}\text{Si}_7$ will represent the true materials properties of $\text{Li}_{12}\text{Si}_7$.

Table 1. Elemental composition of $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ determined by ICP-MS.

Alloy	Expected Li wt.% ^a	Li wt.%	Mo wt.%
$\text{Li}_{12}\text{Si}_7$	29.8	28.6 ± 1.5	1.8 ± 0.5
$\text{Li}_{22}\text{Si}_5$	52.1	52.5 ± 1.1	—

^aOkamoto, H. *Journal of Phase Equilibria and Diffusion* 30, 2009, 118–119.

3.3 Microstructural Analysis

Optical microscopy showed that the $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ microstructures were homogeneous over the entire polished area of the granule. Each alloy is fully dense with no porosity and no second phases show (figure 2). In addition, figure 2 shows that the grain structure of $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$ are fairly equiaxed, with grain sizes of 4 ± 1 and 25 ± 3 μm , respectively.




Figure 2. Optical images of etched samples (a) $\text{Li}_{12}\text{Si}_7$ and (b) $\text{Li}_{22}\text{Si}_5$.

4. Conclusion

A method to synthesize and prepare the Li-Si alloys, $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$, for mechanical testing was developed. Analysis of these alloys using x-ray diffraction and ICP-MS showed that the alloys were single phase $\text{Li}_{12}\text{Si}_7$ and $\text{Li}_{22}\text{Si}_5$. Optical microscopy confirmed the homogeneity of the microstructure of each alloy.

5. References

1. Zhang, W. J. *J. Power Sources* **2011**, *196*, 13–24.
2. Tarascon, J. M.; Armand, M. *Nature* **2001**, *414*, 359–367.
3. Kasavajjula, U.; Wang, C. S.; Appleby, A. *J. J. Power Sources* **2007**, *163*, 1003–1039.
4. Arico, A. S.; Bruce, P.; Scrosati, B.; Tarascon, J. M.; Van Schalkwijk, W. *Nat. Mater.* **2005**, *4*, 366–377.
5. Shenoy, V. B.; Johari, P.; Qi, Y. *J. Power Sources* **2010**, *195*, 6825–6830.
6. Cheng, Y. T.; Verbrugge, M. W. *Electrochem. Solid State Lett.* **2010**, *13*, A128–A131.
7. Kim, H.; Chou, C. Y.; Ekerdt, J. G.; Hwang, G. S. *J. Phys. Chem. C* **2011**, *115*, 2514–2521.
8. Chevrier, V. L.; Zwanziger, J. W.; Dahn, J. R. *Can. J. Phys.* **2009**, *87*, 625–632.
9. Ratchford, J. B.; Schuster, B. E.; Crawford, B. A.; Lundgren, C. A.; Allen, J. L.; Wolfenstine, J. *J. Power Sources* **2011**, *196*, 7747–7749.
10. unpublished results, Ratchford, J.B. et al. 2011
11. Okamoto, H. *Journal of Phase Equilibria and Diffusion* **2009**, *30*, 118–119.
12. Barrett, C. R.; Nix, W. D.; Tetelman, A. S. *The Principles of Engineering Materials*; Printice-Hall, Inc., 1973.

NO. OF COPIES	ORGANIZATION
1 ELEC	ADMNSTR DEFNS TECHL INFO CTR ATTN DTIC OCP 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1 CD	OFC OF THE SECY OF DEFNS ATTN ODDRE (R&AT) THE PENTAGON WASHINGTON DC 20301-3080
1	US ARMY RSRCH DEV AND ENGRG CMND ARMAMENT RSRCH DEV & ENGRG CTR ARMAMENT ENGRG & TECHNLY CTR ATTN AMSRD AAR AEF T J MATTS BLDG 305 ABERDEEN PROVING GROUND MD 21005-5001
1	US ARMY INFO SYS ENGRG CMND ATTN AMSEL IE TD A RIVERA FT HUACHUCA AZ 85613-5300

NO. OF COPIES	ORGANIZATION
1	COMMANDER US ARMY RDECOM ATTN AMSRD AMR W C MCCORKLE 5400 FOWLER RD REDSTONE ARSENAL AL 35898-5000
1	US GOVERNMENT PRINT OFF DEPOSITORY RECEIVING SECTION ATTN MAIL STOP IDAD J TATE 732 NORTH CAPITOL ST NW WASHINGTON DC 20402
5	US ARMY RSRCH LAB ATTN IMNE ALC HRR MAIL & RECORDS MGMT ATTN RDRL CIM L TECHL LIB ATTN RDRL CIM P TECHL PUB ATTN RDRL SED C C LUNDGREN ATTN RDRL SED C J RATCHFORD ADELPHI MD 20783-1197

INTENTIONALLY LEFT BLANK.